

PT - TOUCH (CHOCOLATE)

CARACTERÍSTICAS TÉCNICAS	VALOR/RESULTADO	MÉTODO USADO (NORMAS EN)
ABSORÇÃO DE ÁGUA, % PESO	1,08	BS 680 PT 2
TESTE DE MOLHA E SECAGEM	NENHUM SINAL DE DELAMINAÇÃO/RACHAS AO LONGO DAS ARESTAS, QUANDO EXAMINADAS ATRAVÉS DE UMA LENTE; NEM DE LASCAR-SE DA SUPERFÍCIE.	BS 680 PT 2
TESTE DE IMERÇÃO EM ÁCIDO SULFÚRICO	NENHUM SINAL DE DELAMINAÇÃO AO LONGO DAS ARESTAS, QUANDO EXAMINADAS ATRAVÉS DE UMA LENTE; NEM DE REACÇÕES COMO INCHAR, AMACIAR OU LASCAR-SE DA SUPERFÍCIE. NENHUMA EVOLUÇÃO GASOSA REGISTRADA DURANTE A IMERSÃO.	BS 680 PT 2

EN - TOUCH (CHOCOLATE)

TECHNICAL DATA	VALUE/RESULT	TEST METHOD (EN STANDARD)
WATER ABSORPTION, WEIGHT %	1,08	BS 680 PT 2
WETTING & DRYING TEST	NO SIGNS OF DELAMINATION/ SPLITTING ALONG THE EDGES, WHEN EXAMINED THROUGH A LENS, NOR OF FLAKING OF THE SURFACE.	BS 680 PT 2
SULPHURIC ACID IMMERSION TEST	NO SIGNS OF DELAMINATION ALONG THE EDGES, WHEN EXAMINED THROUGH A LENS, NOR OF SWELLING OF SOFTENING OR FLAKING OF THE SURFACE. NO GASEOUS EVOLUTION DURING IMMERSION.	BS 680 PT 2